



MAGNUM SEAL ACRYLIC PRIMER

- ✓ Interior and exterior applications
- ✓ High hiding power
- ✓ Ideal for priming new drywall and other porous surfaces

Recommended for use with MAGNUM COMPOUNDS



www.gpclarkinternational.com

Superior Finishing Products



MAGNUM SEAL ACRYLIC PRIMER

PRODUCT TECHNICAL DATA

REFERENCE

Magnum Seal Acrylic Primer

USAGE

Magnum Seal Acrylic Primer is a fast drying, high hiding acrylic latex universal primer/sealer suitable for most interior and exterior applications, including interior or exterior plaster, drywall, wood, paneling, masonry, and galvanized metal. Ideal for priming new drywall and other porous surfaces. Also recommended for priming glossy surfaces and previous coats of high gloss oil based paints to ensure proper adhesion of latex paints or most oil based paints (except linseed oil). Suitable for blocking out deep or vibrant colors when changing to a light topcoat. Product is free of lead, chromate and mercury.

PRACTICAL COVERAGE

400 sq. ft./gal. (37 sq.m/gal.).

COLOR

White. May be tinted with approved colorants up to 4 oz. per gallon. Adding tinting colorants may extend dry times.

PACK SIZE

19.2 Kg plastic pail and 1 Gallon in metal cans.

PERCENT SOLIDS

By weight 53.2 ± 2.0 %. By volume 33.4 ± 2.0 %.

FLASH POINT

> 200 °F (93 °C) Closed Cup.

TEMPERATURE RANGE

Recommended application temperature 10 °C - 32 °C, maintain minimum temperature of at least 10 °C until completely dry.

STORAGE

Protect from temperature below 35 °F (1.7 °C), direct sunlight, and extreme heat over 120 °F (49 °C).

RECOMMENDED FILM PER COAT

Wet: 3.0 – 4.0 mils.

Dry: 1.0 – 1.2 mils.

FINISH AND GLOSS RATING Flat.

DRYING TIME

Tack free in 30 minutes; To recoat in 1 hour; To hard finish in 24 hours. Addition of tints may extend dry times.

VISCOSITY

at 25 °C, cPs <2,000.

NET WT. PER GALLON

11.6 ± 0.25 lbs./gal.

VOC CATEGORY

2.1 lbs./gal. (250 grams/liter).

CLEAN

Clean up with soap and water.

SURFACE PREPARATION AND APPLICATION

Surfaces must be clean and free of dust, dirt, grease, mildew, soap residue, loose paint, glue size and any other foreign matter. For best results, the cause of any previous paint failure should be corrected before repainting. New plaster or cement surfaces should age at least 30 days before being painted. All repairs, patching, and sanding should be done before primer is applied. Metal surfaces should be primed with a rust inhibitive metal primer before this product is applied. This product can be top-coated after one hour under normal drying conditions. One coat is usually sufficient on most surfaces, although block out of deep or vibrant color may require two coats. Apply directly as supplied by brush, roller or airless sprayer. Reduction is normally not recommended except for use with regular sprayer, use up to 10:1 reduction with clean water.

PRECAUTIONS

Must not be taken internally.
Keep Out Of Reach Of Children.



G.P.Clark International Distribution, L.L.C.
USA - 27906 E. Colbern Road
Lake Lotawana, MO 64086-8423
TEL. +1-877-900 8510
FAX +1-816-774 3777

G.P. Clark, S.A.L.
LEBANON - Halat Factory
P.O.Box 384 Zouk Michael
TEL. +961-9-478 540/1/3/4
FAX +961-9-478 542

G.P. Clark GCC Building Materials Trading L.L.C
UAE-Dubai- Deyaar Barsha Building
First Floor- Office#117
P.O.Box 391998 - Dubai
TEL / FAX +971 - 4 - 399 7399